



MiraFlor Glazetop

Product Technical Data Sheet

MiraFlor Glazetop is a state-of-the-art, high solids, two-component, UV-stable, aliphatic elastomeric polyaspartic resinous coating. Designed to display a low odor during placement and cure, Glazetop exhibits excellent substrate penetration, adhesion and offers fast turn times and return to service. Glazetop does not require the use of special equipment or plural component spray apparatus, and can be easily mixed and applied using conventional protective coating application methods.

Glazetop is ideal for use as a protective finish/sealer coating over polymer –modified, decorative cementitious microtoppings and stamped overlays. It is also an excellent choice for use in vinyl flake and color quartz broadcast system applications. Glazetop is available in clear, factory pigmented formulations, and a tint base that is mixed with Miracote ColorPax-U pigment pack additive to produce a variety of vibrant colors for a protective coating with superior UV stability, gloss retention and weathering characteristics.

WHERE TO USE

- Protective topcoat for cementitious overlays & microtoppings.
- Optional topcoat for quartz and flake broadcast systems.
- Protective coating for concrete, steel and resinous floors.
- Pharmaceutical plants and warehouses
- Hospitals and healthcare facilities
- Prisons and correctional institutions
- Stadiums and arena's
- Shower and locker rooms
- Cafeteria's and food service facilities

ADVANTAGES

- High elongation and tear strengths.
- Excellent chemical and abrasion resistance.
- Displays superior UV resistance and stability.
- Resistant to hot tire pick-up.
- LEED-compliant, low odor and fast cure time.
- Meets USDA, FDA, OSHA standards.
- Available in high gloss and satin finishes.
- Excellent for interior and exterior exposure.
- Accepts synthetic media for slip resistance.
- Minimizes floor care and maintenance costs.

THEORETICAL COVERAGE RATES

225-250 sq. ft. per gal.

PACKAGING and COLORS

Kit Sizes: 1.5 gallon, 3 gallon, 15 gallon
Component A: 1-gal, 2-gal, 5-gal units
Component B: .5-gal, 1-gal, 5-gal units
Available in clear, tint base and nine standard colors
Refer to Miracote Standard Color Chart #543

MIX RATIO

Glazetop Clear:

Comp. A : Comp. B = 2 : 1 by volume.

Glazetop Pigmented:

Comp. A : Comp. B = 2 : 1 by volume.

Glazetop Tint Base:

Comp. A : Comp. B : Colorpax-U = 2 : 1 : .25 by volume.

SHELF LIFE AND STORAGE

One year from the date of manufacture as long as containers remain unopened and material is stored in a protected environment free from moisture, excessive heat, freezing temperatures, and direct sunlight.

TYPICAL PHYSICAL PROPERTIES @ 75F (24C)

Viscosity (mixed).....	850 cps
Solids Content.....	95%
Pot Life 50% RH (1 gallon mass).....	Approximately 25 minutes
Dry Time 50% RHTack Free	6.0 hrs.
	Light Traffic.....8-10 hrs.
Recoat Time.....	6-24 hrs.
Tear Strength	900 lbs/in
Flexibility ASTM D1737	Passes 180 degree bend. 1/8" Mandrel
Tensile Strength ASTM D412	2,400 psi
Tensile Elongation ASTM D412	100%
Taber Abrasion ASTM D4060	8 mg loss (CS17 Wheel. 1000g Load. 1000 Cycles)
Impact Resistance ASTM D2794	Direct.....160in/lbs Reverse.....160in/lbs
Hardness ASTM D2240 Shore A	85-90
Solid Percent by Weight (mixed)	91%
Solid Percent by Volume (mixed)	89%
Gloss ASTM D523	90+
Coefficient of Friction ASTM D2047.....	Dry 0.67 Wet 0.82
Microbial Resistant ASTM G21	Passes Testing 1
Chemical Resistance (Refer to Chemical Resistance Chart)	

OVERVIEW OF INSTALLATION STEPS

• **Surface Preparation** – All surfaces must be clean, sound, dry and free from any bond inhibiting substances including, but not limited to, grease, oil and any other contaminants or loosely adhered materials. For concrete substrates, a minimum surface profile of a CSP-2 or higher is required depending on overall substrate conditions and coating requirements.

• **Mixing** – MiraFlor Glazetop polyaspartic resin components must be mixed mechanically using a low-speed drill (300-450 rpm) until blended with a “Jiffy-type” or similar Miracote-approved mixing paddle. Empty entire contents of component A and component B into a clean mixing vessel. Mix for approximately 3 minutes keeping the mixing head fully immersed at all times. At least once when mixing, stop to scrape down the sides and bottom of the pail to ensure thorough blending of both components. If not mixing full units, each component must be pre-mixed individually ensuring uniformity prior to use. Once completely mixed and in observance of pot life, dispense material immediately from the pail to the substrate.

MiraFlor Glazetop

Product Technical Data Sheet

OVERVIEW OF INSTALLATION STEPS (continued)

Application – Pour out mixed Glazetop in a large ribbon across the properly primed concrete surface or other type of substrate. Spread evenly with a flat squeegee, and back-roll with a high quality, phenolic core, industrial grade 3/16” to 1/4” maximum nap roller to achieve mil consistency.

FOR BEST RESULTS

- Always install a minimum 4’ by 4’ test area site mock up for approval of acceptable color, texture, finish, adhesion, and any other critical requirement acceptable to the owner prior to proceeding with the installation.
- Verify and download current versions of product technical data sheets (PTDS), material safety data sheets (MSDS), and installation guides (IG) at www.miracote.com.
- Protect materials at all times from excessive heat and cold, and pre-condition to room temperature as necessary.
- Regularly check wet film thickness with mil gauge and monitor consumption to ensure correct application rates are obtained.
- The proper application of this product is the sole responsibility of the end user. Job site visits by Miracote representatives are only for the purpose of making recommendations, and do not assume any liability for supervision or quality control.
- Measure surface and ambient temperatures to ensure the material is only applied when temperatures are 50°F (10°C) and rising during placement and cure time.

LIMITATIONS

- Installed product forms a vapor barrier after cure.
- Not intended for use on exterior concrete slabs-on-grade.
- Minimum ambient/substrate temperature of 50°F (10°C).
- Concrete must be minimum age of 21-28 days, depending on curing and drying conditions.
- Maximum allowable moisture vapor transmission (MVT) of 3.0 lbs./1000 sf./per 24 hr. period per ASTM F1869 (CaCl Testing).
- Maximum allowable moisture vapor transmission (MVT) of 75% RH as per ASTM F2170 (RH-Relative Humidity Testing).
- Use MiraPrime MVERS epoxy moisture mitigation primer over concrete substrates that have MVT emissions that exceed these limits.

LIMITED WARRANTY

NO WARRANTY SHALL BE EFFECTIVE UNTIL THE TERMS AND CONDITIONS OF SALE SET FORTH IN CROSSFIELD PRODUCTS CORP. INVOICES ARE MET.

Crossfield Products Corp. warrants to the purchaser of its products that such products are free from manufacturing defect. Crossfield does not warrant or guarantee the workmanship performed by any person or firm installing its products. Crossfield’s obligation under this warranty is limited solely to the original purchaser and solely to the remedy of replacement in kind of any product which Crossfield sold which may prove defective in manufacture within one year from date of installation, provided said product was stored correctly and installed within the product’s shelf life, by the original purchaser and which Crossfield’s examination shall disclose to Crossfield’s satisfaction to be thus defective.

IN NO EVENT SHALL CROSSFIELD PRODUCTS CORP. BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES. THIS WARRANTY IS EXPRESSLY GIVEN IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR USE AND ALL OTHER OBLIGATIONS OR LIABILITIES ON CROSSFIELD’S PART, AND WE NEITHER ASSUME NOR AUTHORIZE ANY PERSON OR PERSONS TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH SALE OF A CROSSFIELD PRODUCT. THIS WARRANTY SHALL NOT APPLY TO ANY OF CROSSFIELD’S PRODUCTS, WHICH HAVE BEEN SUBJECT TO ADULTERATION, ALTERATION ABUSE OR MISUSE. CROSSFIELD PRODUCTS CORP. MAKES NO WARRANTY WHATSOEVER IN RESPECT TO ACCESSORIES, PARTS OR MATERIAL NOT SUPPLIED BY CROSSFIELD PRODUCTS CORP., WHICH ARE USED IN CONNECTION WITH ITS PRODUCTS. THE TERM “ORIGINAL PURCHASER” IN THIS WARRANTY MEANS THAT PERSON, CORPORATION OR ENTITY TO WHOM CROSSFIELD PRODUCTS CORP. SOLD ITS PRODUCTS. ANY ACTION TO ENFORCE ANY WARRANTY OR FOR BREACH OF CONTRACT OR ARISING OUT OF ANY CLAIM AGAINST CROSSFIELD PRODUCTS CORP. SHALL BE COMMENCED AND MAINTAINED ONLY IN A COURT OF COMPETENT JURISDICTION IN THE CONTINENTAL UNITED STATES OF AMERICA. THE PURCHASER ACCEPTS THESE TERMS AND CONDITIONS, AND HEREBY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES.

CAUTION: ALWAYS KEEP OUT OF THE REACH OF CHILDREN.



**Miracote Product Line
Crossfield Products Corp**

www.miracote.com

East Coast Office
140 Valley Road
Roselle Park, NJ 07204
P: (908) 245-2808
F: (908) 245-0659

West Coast Office
3000 E. Harcourt Street
Rancho Dominguez, CA 90221
P: (310) 631-6594
F: (310) 886-9119



**MIR.291
MIRAFLOR GLAZETOP
10-27-2014**