



# Miracote MPC

## Product Technical Data Sheet



Miracote MPC (Multipurpose Protective Coating) is a polymerized, two component, cementitious protective coating that can be applied over a variety of surfaces including concrete, masonry, metal, wood and tile. It consists of a unique rubber-like polymer liquid that is mixed with a proprietary cement and aggregate blend. Miracote MPC is then typically applied in two or more coats by trowel, brush, roller, spray or notched squeegee and back roll.

Designed for both exterior and interior use, Miracote MPC restores and protects concrete surfaces from the consequences of exposure to water and chloride intrusion, freeze thaw damage and carbonation. Miracote MPC is an extremely durable, cost-effective protective coating that is “breathable” and allows for the transmission of inherent moisture vapor within concrete without blistering or delamination. By lowering moisture content within the concrete, Miracote MPC helps reduce the potential for corrosion of steel reinforcement.

### WHERE TO USE

- Concrete restoration and protection projects
- Resurfacing flawed or discolored concrete
- Bridge parapets and abutments
- Concrete elements in marine environments
- Renovations to stadiums and arenas
- Driveways, sidewalks, balconies and breezeways
- Pool decks and patios
- Secondary containment and water tank linings

### ADVANTAGES

- NSF-61 Certified for use in potable water.
- Moisture vapor permeable – reduces potential for corrosion.
- Protects against penetration of water, chlorides and CO<sup>2</sup>.
- Ideal for exterior/interior, pedestrian and vehicular traffic.
- Enhances appearance and curb appeal of concrete & masonry.
- Excellent adhesion to most substrate.
- Extensive choice of colors, textures and patterns.
- Zero VOC – meets LEED point criteria.
- Slip resistance built-in with most application methods.

### COVERAGE RATES

Theoretical coverage per unit:

One coat Application .....	500 sq. ft. @ 1/32” (31.25 mils)
Two Coat Application.....	250 sq. ft. @ 1/16” (62.50 mils)
Three Coat Application.....	166 sq. ft. @ 3/32” (93.75 mils)

Approximate Yield/Unit .....

1.25 cu. ft. (regular powder only)
------------------------------------

Actual consumption rates are dependent on many factors including, but not limited to, substrate texture and porosity, variations in applied thickness and normal allowance for waste.

### PACKAGING and COLORS

MPC Liquid Catalyst Component (5-gallon pail)

MPC Regular Powder, Natural Gray or White\* (55 lb bag)

\*To match Standard Colors requires use of White Powder

MPC Regular Powder, Gray & White Blend (55 lb bag)

MPC Special Custom Blends Available (55 lb bag)

MPC Smooth\*\* Powder, Natural Gray or White (40 lb bag)

\*\*Used only in MPC Microtopping (Refer to Mir. 250 PTDS)

### MIX RATIO

Regular: 5 Gal Liquid Catalyst : 2-bags of MPC Regular Powder.

Smooth: 5 Gal Liquid Catalyst : 2-bags of MPC Smooth Powder.

### SHELF LIFE AND STORAGE

Shelf life will be one year from the date of manufacture as long as containers remain unopened and when material is store in a protected environment that is free from moisture, excessive heat and freezing temperatures, and direct sunlight.

### TYPICAL PHYSICAL PROPERTIES @ 75°F (24°C)

<b>Working Life</b> .....	15-60 minutes (temperature dependent)
<b>Recoat Time</b> .....	1-4 hours or when dry
<b>Open to Traffic</b> .....	12 – 24 hours
<b>Adhesion</b> ASTM C-882, Type 1 .....	515 psi
<b>Tensile Strength</b> ASTM C190 .....	450 psi
<b>Compressive Strength</b> ASTM C109.....	2,440 psi
<b>Water Vapor Permeability</b> ASTM E96 .....	1.96 perms/in
<b>Water Absorption</b> Weight gain of 4” coated concrete cube after 21 days water immersion (CMCH).....	<2%
<b>Freeze-Thaw Resistance – 50 Cycles</b> .....	no scaling/peeling/flaking (Concrete cylinders immersed for 8 hrs in coated salt water solution followed by 16 hrs. of freezing).
<b>Weathering</b> ASTM G23 .....	No visible degradation (Method I Procedure, 60 cycles)
<b>Resistance to Wind Driven Rain</b>	
Fed. Spec. TT-C-558 .....	(8hrs)
Fed. Spec. TT-C-0035 .....	(24hrs)
At 5” water pressure and 60 gal/hr water flow, no water or dampness noted on back of test panels.	
<b>Resistance to Hydrocarbon Substances</b> .....	ASTM D1308 (Spot Open Test) No softening or attack – after 21 days repeated re-application of gasoline, SAE-10 motor oil and jet fuel.
<b>Impact Resistance</b> MIL-D-3134, Para.4.7.3	
2 lb steel ball dropped from 8’ height onto coated steel plate .....	No cracking or detachment
<b>Flammable Properties</b> ASTM E84 .....	Flame spread – 4 Smoke Density – 0
<b>Fire Resistance</b> UL790.....	Complies as Class A
<b>Potable Water Compatibility</b> .....	NSF/ANSI Compliant

### OVERVIEW OF INSTALLATION STEPS

- **Surface Preparation** - All surfaces to be coated must be clean, sound and free from any bond inhibiting substances including, but not limited to, grease, oil and any other contaminants or loosely adhered materials. For concrete substrates, a minimum surface profile of a CSP-3 or higher is required depending on overall substrate conditions and coating requirements. Concrete and other porous or absorptive substrates should be (SSD) **saturated surface dry** with no standing water at the time of the Miracote MPC application to the substrate.

- **Mixing** – Miracote MPC must be mixed mechanically using a low-speed drill with a “Jiffy-type” or similar Miracote-approved mixing paddle in a clean mixing container. Pre-mix Liquid Catalyst first to re-disperse any polymer solids that may have settled on the bottom of the pail.

When mixing Miracote MPC always pour the liquid catalyst component into the mixing pail first and slowly add the powder component. The mix ratio of powder to liquid may be slightly modified depending on whether a slurry or trowel-grade consistency is desired. Thoroughly mix the Miracote MPC until a uniform smooth consistency is achieved that is free of lumps and pockets of dry powder.

# Miracote MPC

## Product Technical Data Sheet

### OVERVIEW OF INSTALLATION STEPS (Continued)

- **Application** - Miracote MPC can be applied using a roller, brush, broom, trowel, magic trowel, squeegee or spray equipment. Apply Miracote MPC only on properly prepared substrates, and be sure that all voids and bug holes are properly filled by working material into the substrate.

### FOR BEST RESULT

- Always install a minimum 4' by 4' test area or job site mock up for owner approval of acceptable color, texture, finish adhesion and any other critical requirements prior to proceeding with the installation.
- Verify that the most current versions of product technical data sheets (PTDS), material safety data sheets (MSDS), and installation guidelines (IG) are being utilized for project submittals and application reference.
- Protect materials at all times from excessive heat and cold.
- Regularly check wet film thickness with mil gauge and monitor product consumption to ensure correct application thicknesses are obtained.
- The proper application of this product is the sole responsibility of the end user. Job site visits by Miracote representatives are only for the purpose of making recommendations. Supervision and quality control are the sole responsibility of the user.
- Measure surface and ambient temperatures to ensure that material is only applied when surface temperatures range between 40°F (4.5°C) and 90°F (32.2°C) during mixing, placement and time of application.
- As with concrete and other cementitious or masonry products, surface staining and ire marking may occur. Apply a clear film-forming or penetrating sealer to enhance stain resistance, cleanability and minimize tire marking.
- Natural gray and pigmented cementitious coatings may exhibit color variegation due to fluctuating evaporation rates during cure. For better color consistency, apply a topcoat of MiraGard Colorbond or other Miracote pigmented topcoats.

### LIMITATIONS

- May reflect moving cracks and control joints. Implement detail as per current published installation guidelines (IG's).
- Staining, streaking and efflorescence may occur when fresh coating is exposed to excessive ponding or running water.
- Prevent any contact with aluminum which can cause an adverse reaction due to Miracote MPC's cementitious content.

### LIMITED WARRANTY

NO WARRANTY SHALL BE EFFECTIVE UNTIL THE TERMS AND CONDITIONS OF SALE SET FORTH IN CROSSFIELD PRODUCTS CORP. INVOICES ARE MET.

Crossfield Products Corp. warrants to the purchaser of its products that such products are free from manufacturing defect. Crossfield does not warrant or guarantee the workmanship performed by any person or firm installing its products. Crossfield's obligation under this warranty is limited solely to the original purchaser and solely to the remedy of replacement in kind of any product which Crossfield sold which may prove defective in manufacture within one year from date of installation, provided said product was stored correctly and installed within the product's shelf life, by the original purchaser and which Crossfield's examination shall disclose to Crossfield's satisfaction to be thus defective.

IN NO EVENT SHALL CROSSFIELD PRODUCTS CORP. BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES. THIS WARRANTY IS EXPRESSLY GIVEN IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR USE AND ALL OTHER OBLIGATIONS OR LIABILITIES ON CROSSFIELD'S PART, AND WE NEITHER ASSUME NOR AUTHORIZE ANY PERSON OR PERSONS TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH SALE OF A CROSSFIELD PRODUCT. THIS WARRANTY SHALL NOT APPLY TO ANY OF CROSSFIELD'S PRODUCTS, WHICH HAVE BEEN SUBJECT TO ADULTERATION, ALTERATION ABUSE OR MISUSE. CROSSFIELD PRODUCTS CORP. MAKES NO WARRANTY WHATSOEVER IN RESPECT TO ACCESSORIES, PARTS OR MATERIAL NOT SUPPLIED BY CROSSFIELD PRODUCTS CORP., WHICH ARE USED IN CONNECTION WITH ITS PRODUCTS. THE TERM "ORIGINAL PURCHASER" IN THIS WARRANTY MEANS THAT PERSON, CORPORATION OR ENTITY TO WHOM CROSSFIELD PRODUCTS CORP. SOLD ITS PRODUCTS. ANY ACTION TO ENFORCE ANY WARRANTY OR FOR BREACH OF CONTRACT OR ARISING OUT OF ANY CLAIM AGAINST CROSSFIELD PRODUCTS CORP. SHALL BE COMMENCED AND MAINTAINED ONLY IN A COURT OF COMPETENT JURISDICTION IN THE CONTINENTAL UNITED STATES OF AMERICA. THE PURCHASER ACCEPTS THESE TERMS AND CONDITIONS, AND HEREBY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES.

**CAUTION: ALWAYS KEEP OUT OF THE REACH OF CHILDREN.**



**Miracote Product Line  
Crossfield Products Corp**

[www.miracote.com](http://www.miracote.com)

**East Coast Office**  
140 Valley Road  
Roselle Park, NJ 07204  
P: (908) 245-2808  
F: (908) 245-0659

**West Coast Office**  
3000 E. Harcourt Street  
Rancho Dominguez, CA 90221  
P: (310) 631-6594  
F: (310) 886-9119



**MIR.010  
MIRACOTE MPC  
01-12-2018**