



MiraPrime Aqua-Blok XL

Product Technical Data Sheet

MiraPrime Aqua-Blok XL is a clear, single component, odorless, water-based, penetrating colloidal silicate liquid primer that integrally waterproofs concrete, mortar, and other cementitious materials. Based on scientifically superior inorganic mineral waterproofing technology, *Aqua-Blok XL* penetrates deep into the capillary structure of concrete and mortar to permanently enhance physical properties and the dynamics of

waterproofing performance. Exhibiting highly reactive and hydrophilic properties, *Aqua-Blok XL* quickly migrates through waterways and capillary tracts to chemically convert free water-soluble calcium hydroxide into a dense crystalline network of insoluble calcium silicate hydrate within the concrete pore structure. This conversion process has been found to purge unwanted chlorides and other contaminants from the concrete matrix. As determined by the U.S. Bureau of Reclamation M-82 Standard Protocol to Evaluate the Mitigation of Corrosion Technologies in Concrete Repair, *MiraPrime Aqua-Blok XL* substantially reduced corrosion at a 95% Confidence Limit.

WHERE TO USE

- Concrete pool shells and water features.
- Water and wastewater treatment structures.
- Water reservoirs and containment pits.
- Concrete slabs, walls, and foundations.
- Underground vaults and elevator pits.
- Dams, spillways, and tunnels.
- Retaining walls and basements.
- Parking structure slabs, columns, and walls.
- Concrete bridge decks and sub-structures.
- Sidewalks, balconies, and breezeways.
- Commercial and industrial flooring.
- Masonry and stone structures.

ADVANTAGES

- Deep penetration into concrete substrates 2" – 4".
- Water thin micro-crystalline technology – penetrates fast.
- Purges/expels embedded chlorides and blocks re-entry.
- Enhances concrete physical properties – maintains breathability.
- Significantly reduces migration of efflorescence.
- Application from positive or negative side.
- Significantly reduces moisture vapor emissivity.
- Hydrophilic moisture barrier – resists hydrostatic pressures.
- Permanent and self-healing integral waterproofing.
- Enhanced protection of reinforcing steel to corrosion
- Meets USDA standards for non-incident food contact.
- Will not sustain mold, mildew, or fungal growth.
- Non-toxic, low odor and environmentally safe.
- Cures, seals, densifies, and hardens new/existing concrete.

THEORETICAL COVERAGE RATES**

Fresh Concrete:

First Application 150 - 200 sq. ft. per gallon
Second Application 150 - 200 sq. ft. per gallon

Cured Profiled Concrete:

First Application 50 - 250 sq. ft. per gallon
Second Application 50 - 250 sq. ft. per gallon

**A minimum of two applications is required for maximum function/protection. Consumption rates are dependent on many factors including substrate profile, porosity, and water cement ratio. Above rates of application represent typical values.

PACKAGING and COLORS

1-gallon can, 5-gallon pail
Color: Clear

MIX RATIO

Single component – ready to use.

SHELF LIFE AND STORAGE

Two years from the date of manufacture when unopened and material is stored in a protected environment free from moisture, excessive heat, freezing temperatures, and direct sunlight.

TYPICAL PHYSICAL PROPERTIES @ 75°F (24°C)

Vehicle Type.....	Water-based solution
Color	Clear
Flash Point.....	None
Flammability	None
Odor.....	None
pH.....	11 - 12
Weight per gallon.....	9.2 lbs./4.17 kg
Specific Gravity.....	1.10
VOC (grams/liter).....	0.0
Drying Time	2-3 hours

OVERVIEW OF INSTALLATION STEPS

• **Surface Preparation – Fresh Concrete:** Upon removal of concrete formwork or thorough evaporation of all bleed water, concrete surfaces require no specific surface preparation procedures other than rinsing with water at low pressure to remove any form release compounds or other pore blocking substances that may have been applied to concrete surfaces or formwork.

• **Surface Preparation – Cured Concrete:** Take a pH reading of the concrete substrate first by mechanically abrading off a layer of cement paste to remove what has likely become carbonated due to exposure from moisture and carbon dioxide. Ideal range of pH below abraded surface should be a minimum of 10 or higher. For anything under a pH of 10, MiraPrime Concrete Conditioner must be used in conjunction with *Aqua-Blok XL*. All surfaces to be treated must be clean with an open-pore structure to provide access to the capillary network within the concrete matrix. Concrete substrates need to be free from any substances that may inhibit penetration including, but not limited to, grease, oil, sealers, paint, curing compounds, form release agents, adhesives, mildew, algae, fungus, and other foreign matter. If subsequent surface coatings will be applied, a minimum surface profile of CSP-3 or higher is required as per ICRI surface preparation guidelines.

• **Mixing** – A single component ready to use liquid, *Aqua-Blok XL* should be thoroughly agitated and shaken well before use. Do not alter or dilute in any way and use strictly as supplied in original containers. Mechanical mixing is acceptable but not required. Immediately rinse thoroughly with water and clean up any spillage on surfaces not intended to be treated.

• **Application** – Depending on the type of application, MiraPrime *Aqua-Blok XL* can be applied in a variety of methods including brush, roller, or spray apparatus.

Cure and Seal Fresh Concrete Applications – Apply *Aqua-Blok XL* when surfaces have achieved sufficient set to resist foot traffic.

MiraPrime Aqua-Blok XL

Product Technical Data Sheet

Apply uniformly at the recommended coverage rates per gallon and avoid ponding of material in slab depressions and low lying areas. When applying to vertical surfaces use low pressure sprayers (40 psi) with a fan tip nozzle or a minimum 3/8" nap roller and begin applying from the bottom and work up the vertical face with north/south and east/west spray patterns. Saturate the host surface thoroughly until excess material forms a rundown pattern of 6 to 8 inches below the spray contact point. On horizontal substrates, apply a flood coat with enough material to maintain a wet condition for 3 to 5 minutes. If material ponds in shallow depressions use a broom or roller to evenly distribute material to surrounding areas. For maximum function and performance on both vertical and horizontal surfaces, a second wet-on-wet application within 20 to 40 minutes is required. Apply the second application at right angles from the first in a crisscross pattern. During hot weather conditions, pre-wet the substrate to saturated surface dry (SSD) state to cool the surface down prior to application.

Cured Concrete Applications - When applying *Aqua-Blok XL* to vertical surfaces use low pressure sprayers (40 psi) with a fan tip nozzle or a minimum 3/8" nap roller and begin applying from the bottom and work up the vertical face with north/south and east/west spray patterns. Saturate the concrete surface thoroughly until refusal and excess material forms a rundown pattern of 6 to 8 inches below the spray contact point. Once the first application has been absorbed immediately apply the second and apply only as much as the surface will readily absorb. Watch for areas that dry out at a faster rate and re-apply, as necessary. On horizontal substrates, apply a flood coat with enough material to maintain a wet condition for 3 to 5 minutes. If material ponds in shallow depressions use a broom or roller to evenly distribute material to surrounding areas. For maximum function and performance on both vertical and horizontal surfaces, a second wet-on-wet application within 20 to 40 minutes is required. During hot weather conditions, pre-wet the substrate to saturated surface dry (SSD) state to cool the surface down prior to application. As a final step and approximately 30-40 minutes after the last application of *Aqua-Blok XL*, apply two light mist-coats of potable water to the entire treated surface 30-40 minutes apart. This helps transport any uncured inorganic potassium minerals near the surface and drive them down into the concrete capillaries. This also leaves the near surface concrete pores open for the uninhibited application of subsequent coatings, stains, and sealers.

FOR BEST RESULTS

- Always install a minimum 4' x 4' on-site mockup to verify actual coverage rates, and for approval of acceptable color, texture, finish, adhesion, and any other critical requirement acceptable to the owner prior to proceeding with the installation.
- Verify and download current versions of product technical data sheets (PTDS), material safety data sheets (MSDS), and installation guides (IG) at www.miracote.com.

- Protect materials from excessive heat and cold, and pre-condition to room temperature, as necessary.
- Measure surface and ambient temperatures to ensure the material is only applied when temperatures are 40°F (4.5°C) and rising during placement and cure time.
- When applying *Aqua-Blok XL* to concrete exhibiting excessive hydrostatic activity, as evidenced by saturated and weeping surfaces, vacuum, and dry surfaces and immediately follow up the first application with a second and third application, as required.
- Depending on climatic conditions, density of the treated concrete, and potential for purging of chlorides and other entrapped contaminants, *Aqua-Blok XL* is required to cure for 1-7 days prior to the application of surface applied materials.
- Prior to applying subsequent surface coatings any contaminants purged from the concrete must be removed by vacuum and cleaning.
- The proper application of this product is the sole responsibility of the end user. Job site visits by Miracote representatives are only for observation and making recommendations and does not assume any liability for supervision or quality control.

LIMITATIONS

- Protect MiraPrime *Aqua-Blok XL* treated surface from rain for a minimum of two hours after final application.
- Protect glass, plant life, aluminum, ceramics, glazed tile, wood vehicles from contact by overspray. Remove with water immediately.
- **Can etch glass**, avoid contact and rinse glass immediately.
- Do not apply if minimum/maximum ambient and substrate temperatures are 40°F (4.5°C) and above 100°F (37.8°C) 24 hours prior to and following application.
- Concrete surface sealers and polymer-modified mixes will inhibit penetration and function of MiraPrime *Aqua-Blok XL*.
- Rebound-laden shotcrete and gunite structures will be deficient in cementitious content to form a proper chemical reaction and full waterproofing potential.

LIMITED WARRANTY

NO WARRANTY SHALL BE EFFECTIVE UNTIL THE TERMS AND CONDITIONS OF SALE SET FORTH IN CROSSFIELD PRODUCTS CORP. INVOICES ARE MET.

Crossfield Products Corp. warrants to the purchaser of its products that such products are free from manufacturing defect. Crossfield does not warrant or guarantee the workmanship performed by any person or firm installing its products. Crossfield's obligation under this warranty is limited solely to the original purchaser and solely to the remedy of replacement in kind of any product which Crossfield sold which may prove defective in manufacture within one year from date of installation, provided said product was stored correctly and installed within the product's shelf life, by the original purchaser and which Crossfield Products examination shall disclose to Crossfield's satisfaction to be thus defective.

IN NO EVENT, SHALL CROSSFIELD PRODUCTS CORP. BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES. THIS WARRANTY IS EXPRESSLY GIVEN IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR USE AND ALL OTHER OBLIGATIONS OR LIABILITIES ON CROSSFIELD'S PART, AND WE NEITHER ASSUME NOR AUTHORIZE ANY PERSON OR PERSONS TO ASSUME FOR US ANY OTHER LIABILITY IN CONJUNCTION WITH SALE OF A CROSSFIELD PRODUCT. THIS WARRANTY SHALL NOT APPLY TO ANY OF CROSSFIELD'S PRODUCTS, WHICH HAVE BEEN SUBJECT TO ADULTERATION, ALTERATION ABUSE OR MISUSE. CROSSFIELD PRODUCTS CORP. MAKES NO WARRANTY WHATSOEVER IN RESPECT TO ACCESSORIES, PARTS OR MATERIAL NOT SUPPLIED BY CROSSFIELD PRODUCTS CORP., WHICH ARE USED IN CONJUNCTION WITH ITS PRODUCTS. THE TERM "ORIGINAL PURCHASER" IN THIS WARRANTY MEANS THAT PERSON, CORPORATION OR ENTITY TO WHOM CROSSFIELD PRODUCTS CORP. SOLD ITS PRODUCTS. ANY ACTION TO ENFORCE ANY WARRANTY OR FOR BREACH OF CONTRACT OR ARISING OUT OF ANY CLAIM AGAINST CROSSFIELD PRODUCTS CORP. SHALL BE COMMENCED AND MAINTAINED ONLY IN A COURT OF COMPETENT JURISDICTION IN THE CONTINENTAL UNITED STATES OF AMERICA. THE PURCHASER ACCEPTS THESE TERMS AND CONDITIONS, AND HEREBY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES.

CAUTION: ALWAYS KEEP OUT OF THE REACH OF CHILDREN.



Miracote Product Line
Crossfield Products Corp

www.miracote.com

East Coast Office
140 Valley Road
Roselle Park, CA 07204
P: (908) 245-2800
F: (908) 245-0659

West Coast Office
3000 E. Harcourt Street
Rancho Dominguez, CA 90221
P: (310) 631-6594
F: (310) 886-9119



MIRAPRIME AQUA-BLOK XL
12-4-2020