

Installation Guideline

MiraTop SLB 100% Broadcast System

Step#	Installation Steps	Installation Methods	Products & Mix Ratios	Theoretical Coverage Rates
	Mechanically Prepare Substrate Note: Minimum (CSP) concrete surface profile of CSP 3 or higher is required depending on	a. Sandblasting or b. Shotblasting or c. Diamond grinding or d. Other similar and approved	MiraTop SL must be applied to a clean, sound, and mechanically prepared concrete substrate, as per ICRI's Technical Guideline No.310.2R-2013 "Selecting and Specifying Concrete Surface Preparation for Sealers, Coatings, Polymers Overlays and Concrete Repair"	N/A
	substrate conditions & coating requirements.	mechanical methods.	Concrete surface must be dry during application.	
	Optional Skim Coat	a. Trowel applied	Blend MiraPatch RM 2 Liquid and Powder	Yield: .38 CF/Unit
2	(for application over porous or irregular substrates)	b. Squeegee applied	Mix Ratio: (1) Gal Liquid to (1) 40 LB Bag	Covers: 146.2 SF @ 1/32"
				73.1 SF @ 1/16"
	Sawcut Keyways into Concrete Substrate	a. Hand-held angle grinder	To anchor MiraTop SL flooring system into the concrete slab, sawcut	
3		b. Walk-behind saw	1/4" x 1/4" keyways into the substrate a maximum of 4" away from all transitions, terminations and perimeters icluding drains and floor joints.	N/A
			transitions, terminations and perimeters icliding drains and noor joints.	
	Apply MiraTop SL Broadcast Coat	a. Gauge rake & porcupine roll	Blend MiraTop SL	2 Gal. Kit: 40 SF @ 3/16"
			Mix Ratio: Mix entire kit only	30 SF @ 1/4"
4			Kit Sizes: 2 Gal. & (1) 47# Bag of Powder, 4 Gal. & (2) 47# Bags of Powder	
			*Do Not Split Kits	4 Gal. Kit: 80 SF @ 3/16"
			Pot Life - 20 minutes Cure Time - 6 hours Recoat Time - 6 to 48 hours	60 SF @ 1/4"
5	Broadcast #30 Silica Aggregate to Rejection	a. Hand or machine applied	N/A	0.75 lbs. per SF
6	Remove Excess and Loose Aggregate	a. Scraper or Blade Smoother	N/A	N/A
	Apply MiraTop UCS Topcoat	a. Squeegee and Backroll	Blend MiraTop UCS	
			Mix Ratio: Mix entire kit only	100 SF/Kit
			Kit Sizes: 2.3 Gal. & (1) 10# Bag of Powder	35 - 40 mils WFT
7	Note: It is important to maintain a wet edge		*Do Not Split Kits	
	when applyinging topcoats coats & finishes.		Pot Life - 20 minutes Cure Time - 6 hours Recoat Time - 6 to 48 hours	

Note:

Prior to starting the application of any Miracote Product or System be sure to read the Installation Guide(s), Product Data Sheets, MSDS and other pertinent documents published by Crossfield Product Corp. for information, including but not limited to, Precautions, Limitations, Disclaimers and Warranties.



Pay special attention to substrate moisture content, physical condition of the substrate, method(s) of surface preparation, surface restoration, detailing of cracks, joints, transisitions and any applicable specifications. Review carefully for unknown site conditions or defects.

The theoretical coverage rates stated in the Installation Guides are for estimating purposes only. Factors, such as, allowance for material waste, unusual or abnormal substrate conditions and other unforeseen job site conditions that may affect actual product yields are the responsibility of the installer.