



Installation Guideline

Miracote MiraFlex XL - Pedestrian Waterproofing System over Concrete

Step #	Installation Step	Installation Methods	Products & Mix Ratios	Theoretical Coverage Rates
Concrete Surface Preparation				
1	Mechanically Prepare Concrete Substrate Note: Minimum (CSP) concrete surface profile of CSP-3 or higher is required depending on substrate conditions, vehicular traffic exposure and protective coating requirements.	a. Shotblasting or b. Sandblasting or c. Other similar and approved mechanical methods.	Miracote MiraFlex XL System must be applied to a clean, sound, and mechanically prepared concrete surface in accordance with ICRI Technical Guide No.0310.2R-2013 for concrete surface preparation. Concrete substrate can be (SSD) Saturated Surface Dry with no standing water at the time of application as detailed in Step 4.	N/A
1.1	Optional - Apply MiraPrime Aqua-Blok XL. (Not mandatory, but highly recommended to mitigate potential for moisture and efflorescence migration, apply in accordance with applicable PTDS and IG's.			
2	Prime Metal Flashing with MiraFlex Membrane B	a. Brush or b. Roll	MiraFlex Membrane B (Single Component)	400 Ln Ft per gallon
Treatment of Cracks and Cold Joints				
3	Cracks and Cold Joints - 1/16" and Greater 3a - Rout & Seal with Polyurethane Sealant 3b - Apply detail coat of MiraFlex Membrane C Note 1: Rout cracks to create a 3/8" slot, and seal with polyurethane sealant, as per manufacturer recommendations. Broadcast sand into tacky sealant to refusal. Note 2: Apply MiraFlex Membrane C detail coat over over routed cracks a minimum 2" on either side after sealant has fully cured for a minimum 24 to 48 hrs.	a. Medium Nap Roller b. Brush c. Trowel	Blend: MiraFlex Membrane C Liquid and MiraFlex Membrane C Powder Mix Ratio: MiraFlex Membrane C Liquid - (1) 2 Gal.Pail MiraFlex Membrane C Powder - (1) 43 lb bag = 1 Unit Apply a 30 mil WFT detail coat of mixed MiraFlex Membrane centered over the crack and allow to thoroughly dry before proceeding to Step #4.	256 lineal feet per Unit
Waterproofing Membrane Application				
4	Mix and Apply MiraFlex Membrane C First Coat 30 mils WFT (Approx. 1/32")	a. Trowel or b. Squeegee or c. Dip-N-Roll	Blend: MiraFlex Membrane C Liquid and MiraFlex Membrane C Powder Mix Ratio: MiraFlex Membrane C Liquid - (1) 2 Gal.Pail MiraFlex Membrane C Powder - (1) 43 lb bag = 1 Unit Miracote Poly Fabric Reinforcement: Apply a 30 mil WFT Scrub Coat of mixed MiraFlex Membrane C onto the concrete surface, and immediately embed Miracote Poly Fabric	Yield: 160 sq. ft/Unit Application Thickness: 30 mils WFT (Approx. 1/32")
5	Mix and Apply MiraFlex Membrane C Second Coat Embedded into Poly Fabric Reinforcement 30 mils WFT (Approx. 1/32")	a. Trowel or b. Squeegee or c. Dip-N-Roll	Blend: MiraFlex Membrane C Liquid and MiraFlex Membrane C Powder Mix Ratio: MiraFlex Membrane C Liquid - (1) 2 Gal.Pail MiraFlex Membrane C Powder - (1) 43 lb bag = 1 Unit	Yield: 124 sq. ft/Unit Application Thickness: 45 mils WFT (Approx. 1/22")



Installation Guideline

Miracote MiraFlex XL - Pedestrian Waterproofing System over Concrete

Step #	Installation Step	Installation Methods	Products & Mix Ratios	Theoretical Coverage Rates
Textured Wearcourse Application				
6	Apply 1st Coat - Miracote MPC Regular	a. Hand Trowel or b. Magic trowel or c. Squeegee	Blend: Miracote MPC Liquid Catalyst and MPC Powder Mix Ratio: 5 Gal Miracote MPC Liquid Catalyst to (2) 55# Bags Note: Climatic conditions that are associated with high rates of evaporation can decrease MPC working time. Add 1 unit of Miracote Retarder to increase valuable working time when these conditions are present or anticipated. Mix Option 1 (Not Pigmented) Mix Gray or White Regular MPC Mix Option 2 (Pigmented) Mix Gray or White Regular MPC with (1) ColorPax-LIP Unit	500 SF/Unit 30 mils +/-
7	Apply 2nd Coat - Miracote MPC Regular Note: Refer to the appropriate MPC Installation Guideline for the desired final finish or texture, i.e. Knockdown, Broom, Stipple, Stencil/Tape Pattern.	a. Hand Trowel or b. Magic trowel or c. Squeegee or d. Hopper Gun or e. Similar spray method (Low Pressure 8 -15 psi)	Same as above	Same as above Note: MPC coverage rate can vary depending on the desired texture of finish, and the profile or condition of the existing concrete substrate.
Acrylic Topcoat Application				
8	Apply 2 Top Coats of MiraGard Colorbond XL (Required for Specification Compliance)	a. Dip and Roll or b. Airless Spray	MiraGard Colorbond XL Single Component	250 - 300 SF/Gal Note: MiraGard Colorbond XL coverage rate can depend on the desired texture of wearcourse.
Apply Clear Sealer to Enhance Stain Resistance & Cleanability (one or two coats) - Optional when MiraGard Colorbond XL is Used				
9	Choose any of the Miracote sealers or topcoats for best results depending on location, service, use and exposure. Refer to the Product Technical Data Sheets and Installation Guides for Miracote MiraGard HDWB, MiraGard HD 400, MiraGard HD 100 or MiraThane WB.			

Note: Prior to starting the application of any Miracote Product or System be sure to read the Installation Guide(s), Product Data Sheets, MSDS and other pertinent documents published by Crossfield Product Corp. for information, including but not limited to, Precautions, Limitations, Disclaimers and Warranties.



Pay special attention to substrate moisture content, physical condition of the substrate, method(s) of surface preparation, surface restoration, detailing of cracks, joints, transitions and terminations, and any applicable specifications. Review carefully for unknown site conditions or defects.

The theoretical coverage rates stated in the Installation Guides are for estimating purposes only. Factors, such as, allowance for material waste, unusual or abnormal substrate conditions and other unforeseen job site conditions that may affect actual product yields are the responsibility of the installer.