



# MiraFlor Epoxy

## Chemical Resistance Chart

Chemical Name	EPOXY	
	MiraFlor CR-N	MiraFlor CQ
Acetone	A	B
Ammonium Hydroxide <30%	B	C
Ammonium Hydroxide 10%	B	B
Antifreeze (Propylene glycol)	A	B
Chlorine (5000 ppm)	A	C
Chlorine Water	A	B
Citric Acid 10%	A	B
Cottage Cheese	A	A
Ethylene Glycol	A	B
Fatty Acids	A	B
Glycerine	A	B
Hydraulic Oil	A	C
Hydrobromic Acid <50%	A	C
Hydrochloric Acid <70%	B	C
Hydrochloric Acid 10%	B	C
Isopropyl Alcohol	A	C
Ketchup	A	B
Methyl Ethyl Ketone	B	C
Methylene Chloride	B	C
Milk	A	A
Mineral Oil	A	A
Mustard	A	B
Mustard	A	A
Nitric Acid >30%	B	C
Phosphoric Acid 10%	A	C
Phosphoric Acid 50%	B	C
Red Wine	A	B
Skydrol	A	C
Sulphuric Acid 10%	A	C
Sulphuric Acid 70%	A	C
Toluene	A	C
Turbo Oil	A	C
Vegetable Oil	A	B
Vinegar	A	C
Water	A	A
Whiskey	A	B
Xylene	A	C

A = Suitable for environments including immersion

B = Suitable for spills & splashes, but not immersion

C = Unsuitable for exposure to this chemical

All testing was done in accordance with ASTM D1308 at 75°F and 50% RH.

For further testing of chemicals not listed, please contact your local Miracote Representative.