



Mortar Bed 2000

Product Technical Data Sheet

Mortar Bed 2000 is a single component, polymer-modified, pre-blended cementitious mortar bed fortified with micro-fiber reinforcement and shrinkage-compensating additives to achieve exceptional physical properties with very low drying shrinkage. Designed for horizontal and vertical applications, **Mortar Bed 2000** can be hand-troweled to create a thin-to-thick mortar bed from 1/8" up to 1". Does not require the use of a separate latex admixture for mixing. You only need to add 3.5 quarts of potable water to produce a superior, one-step mortar bed that does not require the application of a slurry coat to the concrete substrate.

WHERE TO USE

- Interior and exterior, in wet or dry applications.
- For thin or thick mortar bed – bonded or unbonded.
- Concrete surface repairs and flooring underlayment.
- Wall rendering and floor sloping mortar.
- Rapid return to service requirements – high early strength.

ADVANTAGES

- Polymer modified powder – no need liquid latex admixture.
- Factory premixed blend – no batching on site, lime free.
- High early strength – 2,000 psi in 4 hours.
- Rapid return to service for fast-track installations.
- Very low water absorption and drying shrinkage.
- Excellent compressive, flexural and tensile strengths.
- Tenacious adhesion to prepared substrates.
- Meets requirements of ANSI A108.1

COVERAGE RATES

Theoretical coverage rate per 50 lb. bag:

- 46.6 sq. ft. @ 1/8"
- 23.3 sq. ft. @ 1/4"
- 17.4 sq. ft. @ 3/8"
- 11.6 sq. ft. @ 1/2"
- 4.8 sq. ft. @ 1"

Approximate Yield/Bag - .48 cu. ft.

Actual consumption rates are dependent on many factors including, but not limited to, substrate texture and porosity, variations in applied thickness and normal allowance for waste.

PACKAGING and COLORS

Powder (50-pound bag) - Available in gray.

MIX RATIO

3.5 Quarts Potable Water to (1) 50 lb. bag of powder.

SHELF LIFE AND STORAGE

One year from the date of manufacture provided packaging remains unopened and material is stored in a protected environment free from moisture, excessive heat, freezing temperatures, and direct sunlight.

TYPICAL PHYSICAL PROPERTIES @ 75°F (24°C)

Water Demand	Approximately 3.5 to 3.75 quarts/bag
Working Time	40 minutes (with cool mix water)
Compressive Strength (ASTM C109):	
4 Hour	2,225 psi
1 Day	3,175 psi
7 Day	5,575 psi
28 Day	6,125 psi
Tensile Strength (ASTM C190):	
7 Day	435 psi
28 Day	585 psi
Flexural Strength (ASTM C348):	
7 Day	845 psi
28 Day	1,400 psi
Adhesion (ACI 503.R)	> 290 psi
Water Absorption (ANSI A118.7)	< 4.0%
Shrinkage (ASTM C157)	<.04 %
Initial Set (ASTM C191)	31 min.
Final Set (ASTM C191)	39 min.

OVERVIEW OF INSTALLATION STEPS

- **Surface Preparation** – All surfaces must be clean, sound, and free from bond inhibiting substances including, but not limited to, grease, oil and any other contaminants or loosely bonded materials. Follow ICRI Technical Guideline #310.2-1997 for detailed surface preparation requirements. A minimum surface profile of a CSP-4 or higher is required depending on overall substrate conditions and concrete repair requirements. Concrete and other porous or absorptive substrates must be **(SSD) saturated surface dry** with no standing water at the time of application.

- **Mixing Mortar Bed 2000** – **Mortar Bed 2000** must be mixed mechanically to a uniform consistency in a clean mixing vessel using a low-speed drill (300-450 rpm) with a “Jiffy-type” or similar Miracote-approved mixing paddle. Pour approximately 3.5 quarts of potable water into the mixing vessel. When mixing always add the powder component gradually to the mix water. Thoroughly blend the complete unit for a minimum of two minutes. For desired consistency, you may add an additional 1/4 quart of potable water and continue mixing one more minute or until a uniform homogeneous consistency is achieved.

Mortar Bed 2000

Product Technical Data Sheet

OVERVIEW OF INSTALLATION STEPS (continued).

Application & Finish – As with all trowel-grade repair mortars, *Mortar Bed 2000* must be applied to a saturated surface dry (SSD) substrate with no standing water. To ensure intimate contact with the concrete substrate, apply a scrub coat to fill all pores and voids and place repair mortar immediately while scrub coat is still wet. Trowel the mortar against the perimeter of the repair and work the material toward the center. To complete the repair, finish surface with appropriate trowel or float as required depending on desired surface texture. Do not re-temper the material when it is no longer workable.

FOR BEST RESULTS

- Always install a minimum 4' by 4' test area or job site mockup for owner approval of acceptable color, texture, finish adhesion and any other critical requirements prior to proceeding with the installation.
- Verify that the most current versions of product technical data sheets (PTDS), color charts, material safety data sheets (MSDS), and installation guidelines (IG) are being utilized for project submittals and application reference.
- Protect materials always from excessive heat and cold, and pre-condition material as required in adverse conditions.
- As per ACI recommendations for Portland cement concrete, curing is required to meet published physical properties. Moist curing with burlap/polyethylene or burlene is the preferred method. A compatible water-based curing compound is also acceptable but may require removal prior to the application of subsequent coatings or other materials.
- The proper application of this product is the sole responsibility of the end user. The intent of job site visits by Miracote representatives is for observation of the work and offering technical recommendations only. Supervision and quality control are the sole responsibility of the user.
- Measure surface and ambient temperatures to ensure that material is only applied when both temperatures range between 40°F (7°C) and 90°F (7°C) during mixing, placement and time of application.

LIMITATIONS

- Concrete surface repair dimensions including overall length, width, depth and shape need careful consideration and should be in conformance with ACI recommended standards of practice.
- Mechanical surface preparation methods may require additional testing to verify substrate tensile strength in accordance with ICRI Guideline No. 210.3R-2013 (Guide for Using In-Situ Tensile Pull-off Tests to Evaluate Bond of Concrete Surface Materials).
- Extension with coarse aggregates may alter the physical properties of *Miracote Mortar Bed 2000* as published.
- Do not use solvent based curing compounds.
- As with all cement-based materials, avoid direct contact with aluminum to prevent adverse chemical reactions. Refer to MiraPrime MP for an appropriate primer.

LIMITED WARRANTY

NO WARRANTY SHALL BE EFFECTIVE UNTIL THE TERMS AND CONDITIONS OF SALE SET FORTH IN CROSSFIELD PRODUCTS CORP. INVOICES ARE MET.

Crossfield Products Corp. warrants the purchaser of its products that such products are free from manufacturing defects. Crossfield does not warrant or guarantee the workmanship performed by any person or firm installing its products. Crossfield's obligation under this warranty is limited solely to the original purchaser and solely to the remedy of replacement in kind of any product which Crossfield sold which may prove defective in manufacture within one year from date of installation, provided said product was stored correctly and installed within the product's shelf life, by the original purchaser and which Crossfield's examination shall disclose to Crossfield's satisfaction to be thus defective.

IN NO EVENT, SHALL CROSSFIELD PRODUCTS CORP. BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES. THIS WARRANTY IS EXPRESSLY GIVEN IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR USE AND ALL OTHER OBLIGATIONS OR LIABILITIES ON CROSSFIELD'S PART, AND WE NEITHER ASSUME NOR AUTHORIZE ANY PERSON OR PERSONS TO ASSUME FOR US ANY OTHER LIABILITY IN CONJUNCTION WITH SALE OF A CROSSFIELD PRODUCT. THIS WARRANTY SHALL NOT APPLY TO ANY OF CROSSFIELD'S PRODUCTS, WHICH HAVE BEEN SUBJECT TO ADULTERATION, ALTERATION ABUSE OR MISUSE. CROSSFIELD PRODUCTS CORP. MAKES NO WARRANTY WHATSOEVER IN RESPECT TO ACCESSORIES, PARTS OR MATERIAL NOT SUPPLIED BY CROSSFIELD PRODUCTS CORP, WHICH ARE USED IN CONJUNCTION WITH ITS PRODUCTS. THE TERM "ORIGINAL PURCHASER" IN THIS WARRANTY MEANS THAT PERSON, CORPORATION OR ENTITY TO WHOM CROSSFIELD PRODUCTS CORP. SOLD ITS PRODUCTS. ANY ACTION TO ENFORCE ANY WARRANTY OR FOR BREACH OF CONTRACT OR ARISING OUT OF ANY CLAIM AGAINST CROSSFIELD PRODUCTS CORP. SHALL BE COMMENCED AND MAINTAINED ONLY IN A COURT OF COMPETENT JURISDICTION IN THE CONTINENTAL UNITED STATES OF AMERICA. THE PURCHASER ACCEPTS THESE TERMS AND CONDITIONS, AND HEREBY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES.

CAUTION: ALWAYS KEEP OUT OF THE REACH OF CHILDREN.



Miracote Product Line
Crossfield Products Corp

www.miracote.com

East Coast Office
140 Valley Road
Roselle Park, NJ 07204
P: (908) 245-2808
F: (908) 245-0659

West Coast Office
3000 E. Harcourt Street
Rancho Dominguez, CA 90221
P: (310) 631-6594
F: (310) 886-9119



MORTAR BED 2000
12-10-2024