

# ICC-ES Evaluation Report

**ESR-1714**

Reissued May 2024

Revised January 2025

Subject to renewal May 2025


This report also contains:

- [CA Supplement](#)

- [FL Supplement](#)

ICC-ES Evaluation Reports are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of the subject of the report or a recommendation for its use. There is no warranty by ICC Evaluation Service, LLC, express or implied, as to any finding or other matter in this report, or as to any product covered by the report.

Copyright © 2025 ICC Evaluation Service, LLC. All rights reserved.

<p><b>DIVISION: 07 00 00— THERMAL AND MOISTURE PROTECTION</b></p> <p><b>Section: 07 18 13— Pedestrian Traffic Coatings</b></p>	<p><b>REPORT HOLDER: CROSSFIELD PRODUCTS CORP. - MIRACOTE DIVISION</b></p>	<p><b>EVALUATION SUBJECT: MIRACOTE MIRAFLEX WATERPROOFING DECKING SYSTEMS</b></p>	
--	--	---	---

## 1.0 EVALUATION SCOPE

Compliance with the following codes:

- 2024, 2021, 2018, 2015, 2012, 2009 and 2006 [International Building Code® \(IBC\)](#)
- 2024, 2021, 2018, 2015, 2012, 2009 and 2006 [International Residential Code® \(IRC\)](#)
- 2013 *Abu Dhabi International Building Code (ADIBC)*<sup>†</sup>

<sup>†</sup>The ADIBC is based on the 2009 IBC. 2009 IBC code sections referenced in this report are the same sections in the ADIBC.

Properties evaluated:

- Durability
- Wind resistance
- Fire classification
- Fire-resistance-rated construction

## 2.0 USES

The Miracote Miraflex Waterproofing Decking Systems are walking deck and Class A roof covering systems for use directly over concrete or plywood substrates. The systems may also be used as a component of a one-hour fire-resistance-rated roof assembly as described in Section 4.9 of this report.

## 3.0 DESCRIPTION

### 3.1 General:

Miracote Miraflex Waterproofing Decking Systems are polymer-modified, cementitious walking deck and roof covering systems that consist of expanded metal lath; polymer-modified cementitious mortar base coat; a polymeric waterproofing layer; reinforcing fabric or seam tape; a protection coat; and either a topcoat or a sealer coat. See Section 4.0 and [Tables 1](#) and [2](#) for Miracote Miraflex Waterproofing Decking system configurations and corresponding component requirements.

### 3.2 Materials:

**3.2.1 General:** Miracote Miraflex Waterproofing Decking System's powder and liquid components have a shelf life of one year when stored indoors at temperatures between 40°F and 100°F (4.4°C and 37.8°C). Liquid components must be kept from freezing.

#### 3.2.2 Base Coat Components

**3.2.2.1 MiraPatch RM 1 (Repair Mortar) Powder:** A proprietary dry mixture of Portland cement and graded aggregates supplied in 50-pound (22.7 kg) bags.

**3.2.2.2 MiraPatch RM 3 (Repair Mortar) Powder:** A proprietary dry mixture of Portland cement and graded aggregates supplied in 36-pound (16.4 kg) bags.

**3.2.2.3 MiraPatch LM Powder (Lath Mortar):** A proprietary dry mixture of cement and graded aggregates supplied in 50-pound (22.7 kg) bags.

**3.2.2.4 MiraPatch RM 1 Liquid, MiraPatch RM 3 Liquid and MiraPatch LM Liquid:** Liquid polymers designed to be mixed with their respective MiraPatch RM (Repair Mortars) or MiraPatch LM Powders, supplied in 5-gallon (18.9 L) containers.

### 3.2.3 Waterproofing Layer Component:

**3.2.3.1 MiraFlex Membrane A:** A liquid polymer waterproofing latex supplied in 5-gallon (18.9 L) containers.

**3.2.3.2 Miracote Liquid Membrane:** A liquid polymer waterproofing latex with adhesion promoter supplied in 5-gallon (18.9 L) containers.

**3.2.3.3 Miracote Poly Fabric:** A polypropylene woven-mesh reinforcing fabric available in 40-inch-wide-by-300-foot-long (1.02 by 91.4 m) rolls, weighing 0.45 ounces per square foot (136 g/m<sup>2</sup>).

**3.2.3.4 MiraFlex Seam Tape:** A cold applied, self-adhering membrane composed of a polymer fabric coated on one side with a layer of synthetic butyl, block copolymer. It is primarily used in sealing butt joints and wood to metal flashing transitions and is available in 4-inch-wide by 75-feet-long (101.6 mm by 22 860 mm) rolls.

### 3.2.4 Protection Layer Components:

**3.2.4.1 Miracote Protective Powder:** A dry blend of Portland cement and graded aggregates packaged in 55-pound (25.0 kg) bags.

**3.2.4.2 Miracote MPC Liquid Catalyst:** A liquid polymer designed to be used with Miracote Protective Powder dry mix, supplied in 5-gallon (18.9 L) containers.

**3.2.4.3 Mirastamp Powder:** A dry blend of Portland cement and graded aggregates, packaged in 45-pound (20.5 kg) bags.

**3.2.4.4 Mirastamp Liquid:** A liquid polymer designed to be used with Mirastamp Powder, supplied in 5-gallon (18.9 L) containers.

### 3.2.5 Topcoat Component

**3.2.5.1 Miracote MiraGard Color Bond XL:** A water-borne, pigmented, acrylic topcoat supplied in 5-gallon (18.9 L) containers.

### 3.2.6 Sealer Coat Components:

**3.2.6.1 Miracote MiraGard HDWB:** A waterborne, clear, acrylic sealer supplied in 5-gallon (18.9 L) containers.

**3.2.6.2 Miracote MiraGard Color Bond (XL):** A waterborne, pigmented sealer supplied in 5-gallon (18.9 L) containers.

**3.2.7 Metal Flashing:** Metal flashing must be minimum 0.019-inch-thick [0.48 mm (26 gage)], corrosion-resistant metal. Flashings must be rigid enough to avoid excessive deflection and ponding, or must be solidly backed by the concrete or plywood substrate.

### 3.2.8 Substrates:

**3.2.8.1 Plywood:** Plywood must be minimum <sup>5</sup>/<sub>8</sub>-inch-thick (15.9 mm) exterior-grade plywood complying with U.S. DOC PS-1 or PS-2.

**3.2.8.2 Concrete:** Concrete decks must comply with the applicable requirements of the applicable code and must have a minimum compressive strength (*f<sub>c</sub>*) of 2,500 psi (17.2 MPa).

**3.2.9 Metal Lath:** Metal lath must be minimum 1.8-pound-per-square-yard (1.0 kg/m<sup>2</sup>), galvanized, expanded metal lath complying with ASTM C847.

**3.2.10 Staples:** Staples must be corrosion-resistant, minimum No. 16 gage staples with minimum 1-inch-wide (25.4 mm) crowns and <sup>1</sup>/<sub>2</sub>-inch-long (12.7 mm) legs, complying with ASTM F1667.

## 4.0 INSTALLATION

### 4.1 General:

Installation of the Miracote Miraflex Waterproofing Decking System must be in accordance with the manufacturer's published installation instructions, the applicable code and this report. The manufacturer's installation instructions must be available on the jobsite during application. Installation must only be performed when the weather is dry and the ambient air temperature is between 60°F and 95°F (15.6°C and 35.0°C). Materials must not be applied if precipitation is occurring or expected.

Substrates must be structurally sound, clean and dry, and must be sloped a minimum of <sup>1</sup>/<sub>4</sub> inch per foot (2% slope).

### 4.2 Preparation of Substrates:

**4.2.1 Plywood:** Plywood must be applied to framing in accordance with the requirements of the applicable code. All edges must be blocked. All penetrations through and terminations of the sheathing must be protected with metal flashing in accordance with the requirements of the applicable code and the manufacturer's published installation instructions.

**4.2.2 Concrete:** Surfaces must be clean and free of standing water. All holes, joints and cracks must be pointed flush with Portland cement mortar and all high spots cut or ground off to provide a smooth, even surface. Any foreign material such as paint, grease or oil must be removed by mechanical means. New concrete must be mechanically scarified prior to application of the system.

**4.3 Systems A and B (Installation over Plywood – See Table 1):**

**4.3.1 Metal Lath:** Metal lath, as described in Section 3.2.9 of this report, must be fastened with staples described in Section 3.2.10 to the plywood deck with 22 to 28 staples per square foot (0.09 m<sup>2</sup>), uniformly distributed. Where the metal lath is butt-jointed, the staple spacing at the joint must be no greater than 2 inches (51 mm) on center. Butt joints of metal lath must not occur over plywood joints. Where plywood joints occur, metal lath shall be stapled across all plywood joints at 4 inches (102 mm) on center.

**4.3.2 Base Coat:** The base coat must be one of the following:

- Two one gallons (3.8 L) of MiraPatch RM 1 Repair Mortar Liquid mixed with three 50-pound (34.0 kg) bags of MiraPatch RM I Powder. Coverage must be approximately 84 square feet (7.8 m<sup>2</sup>) per batch at a minimum thickness of <sup>3</sup>/<sub>16</sub> inch (4.8 mm).
- One and a quarter gallon (4.75 L) of MiraPatch 3 Liquid mixed with one 50-pound bag of MiraPatch LM Powder. Coverage must be approximately 43 square feet (3.99 m<sup>2</sup>) per batch at a minimum thickness of <sup>3</sup>/<sub>16</sub> inch (4.8 mm).
- One gallon (3.8 L) of MiraPatch Repair Mortar 3 Liquid mixed with one 36-pound (16.4 kg) bag of MiraPatch RM 3 Powder. Coverage must be approximately 23 square feet (2.1 m<sup>2</sup>) per batch at a minimum thickness of <sup>3</sup>/<sub>16</sub> inch (4.8 mm).

The base coat must be trowel-applied to completely fill and cover the metal lath to a minimum total thickness of <sup>3</sup>/<sub>16</sub> inch (4.8 mm). The base coat must be allowed to cure a minimum of eight hours before application of the waterproofing layer.

**4.3.3 Waterproofing Layer:** MiraFlex Membrane A or MiraFlex Liquid Membrane for better adhesion must be mixed with water at a ratio of 1:1 by volume, and the first coat must be roller-applied over the base coat at a rate of 1 gallon per 400 square feet (1 L/9.8 m<sup>2</sup>). Two additional coats of Membrane A (undiluted) must be applied with a <sup>1</sup>/<sub>8</sub>-inch (3.2 mm) V-notched trowel, at a rate of 1 gallon per 64 square feet (1 L/1.6 m<sup>2</sup>), for a minimum total dry-film thickness of 0.025 inch [25 mils (0.64 mm)] for each coat. Each coat must be allowed to dry to the touch before the next coat is applied [approximately one hour at 70° F (21.0° C)]. Reinforcing fabric poly propylene “Poly Fabric” must be embedded in the final coat and be allowed to cure for a minimum of four hours before application of the protection coat.

**4.3.4 Protection Coat:** Five gallons (18.9 L) of Miracote Liquid Catalyst must be mixed with two 55-pound (25.0 kg) bags of Miracote Protective Coating. Two coats of the protection coat must be applied over the waterproofing layer by trowel or texturing hopper gun at a rate of 1 gallon per 41 square feet (1 L/1.0 m<sup>2</sup>), for a minimum wet-film thickness of 0.039 inch [39 mils (0.99 mm)] for each coat. The first coat must be allowed to dry for four to six hours before the application of the second coat. The second coat must be allowed to cure for a minimum of eight hours before application of the topcoat.

**4.3.5 Topcoat (Required for Systems A and B):** Two coats of Miracote MiraGard Color Bond (XL) must be roller-applied over the protection coat at a rate of 1 gallon per 300 square feet (1 L/7.4 m<sup>2</sup>), for a minimum wet-film thickness of 0.011 inch [11 mils (0.28 mm)] for each coat. The first coat must be allowed to dry for approximately one hour before application of the second coat. The second coat must be allowed to cure for a minimum of eight hours before application of the sealer.

**4.3.6 Sealer (Required for Systems B):** Two coats of Miracote MiraGard HDWB sealer, roller-applied over the protection coat at a rate of 1 gallon per 400 square feet (1 L/9.8 m<sup>2</sup>), for a minimum wet-film thickness of 0.011 inch [11 mils (0.28 mm)] for each coat. The first coat must be allowed to dry for a minimum of 30 minutes before application of the second coat. After application of the second coat, the coating must be allowed to dry for 12 to 24 hours before traffic is allowed on the coating.

**4.4 Systems D, E and F (Installation over Concrete – See Table 2):** Application of the waterproofing layer and protection coat, must be as described in Sections 4.3.3 and 4.3.4, respectively.

For Systems D and E application of the topcoat must be as described in Section 4.3.5.

For Systems D and F application of the sealer must be as described in Section 4.3.6.

**4.5 System G (Installation over Concrete – See Table 2):**

Application of the waterproofing layer and sealer must be as described in Sections 4.3.3 and 4.3.6, respectively.

For application of the protection coat, one gallon (3.8 L) of Mirastamp Liquid must be mixed with a 45-pound (20.5 kg) bag of Mirastamp Powder and applied with a spreader rake and closed with a float trowel over the waterproofing layer at a rate per batch of 18 square feet (1.7 m<sup>2</sup>) for the minimum <sup>1</sup>/<sub>4</sub>-inch (6.4 mm) thickness, 13.5 square feet (1.3 m<sup>2</sup>) for the <sup>3</sup>/<sub>8</sub>-inch (9.5 mm) thickness, or 9 square feet (0.83 m<sup>2</sup>) for a thickness of <sup>1</sup>/<sub>2</sub> inch (12.7 mm). The coating is processed and stamped and allowed to cure for a minimum of 12 hours.

**4.6 Method of Repair:**

The damaged area must be removed and replaced as required for a new installation, as described in Section 4.3, 4.4, or 4.5. When substrate damage occurs, the retention of the fire-resistance rating and strength properties must be investigated, and the results submitted to the code official.

**4.7 Wind Resistance:**

Under the 2024, 2021 and 2018 IBC, the Miracote Miraflex Waterproofing Decking system may be used in areas subject to a basic wind speed (V) of 130 mph (209 km/h) on structures with a maximum height of 40 feet (12,192 mm) in Exposure B areas.

Under the 2015 and 2012 IBC and 2024, 2021, 2018, and 2015 IRC, the Miracote Miraflex Waterproofing Decking system may be used in areas subject to an ultimate design wind speed ( $V_{ult}$ ) of 130 mph (209 km/h) on structures with a maximum height of 40 feet (12,192 mm) in Exposure B areas.

Installation must be limited to areas where the maximum basic wind speed, building height and exposure comply with [Tables 3](#) and [4](#) of this report, as applicable.

#### 4.8 Class A Roof Covering Construction:

When Miraflex Waterproofing Decking systems are applied over concrete or  $5/8$ -inch-thick (15.9 mm) exterior-grade plywood substrates with all edges blocked, the systems have a Class A roof classification, provided the maximum slope does not exceed  $1/2$  inch per foot (4% slope).

#### 4.9 One-hour Fire-resistance-rated Construction:

The Miracote MiraFlex Waterproofing Deck systems described in Section 4.3 of this report, when applied over  $5/8$ -inch-thick (15.9 mm) exterior-grade plywood, with nominally 2-by-10 (51 by 254 mm) joists spaced at 16 inches (406 mm) on center, and all plywood joints blocked, can be recognized as a substitute for the double wood floor described in Item 13 of Table 721.1(3) of the 2024, 2021, 2018, 2015 and 2012 IBC (Table 720.1(3) of the 2019 IBC and 2006 IBC).

## 5.0 CONDITIONS OF USE:

The Miracote Miraflex Waterproofing Decking systems described in this report complies with, or is a suitable alternative to what is specified in, those codes listed in Section 1.0 of this report, subject to the following conditions:

- 5.1 Installation must comply with this report, the manufacturer's published installation instructions and the applicable code. If there is a conflict between the installation instructions and this report, this report must govern.
- 5.2 Installation must be limited to use in areas where the wind speed does not exceed what is specified in [Table 3](#) of this report.
- 5.3 The products are manufactured at the Crossfield Products Corporation facility in Rancho Dominguez, California, under a quality control program with inspections by ICC-ES.

## 6.0 EVIDENCE SUBMITTED

- 6.1 Data in accordance with the [ICC-ES Acceptance Criteria for Walking Decks \(AC39\)](#), dated June 2017 (editorially revised May 2024).
- 6.2 Report of wind resistance testing in accordance with FM Standard 1-52.

## 7.0 IDENTIFICATION

- 7.1 The ICC-ES mark of conformity, electronic labeling, or the evaluation report number (ICC-ES ESR-1714) along with the name, registered trademark, or registered logo of the report holder must be included in the product label.
- 7.2 In addition, each container or bag of the Miracote Miraflex Decking System Walking Deck and Roof Covering components described in this report must be identified by a product label bearing the report holder's name (Crossfield Products Corporation—Miracote Division) and address, product designation, batch number keyed to date of manufacture, and product expiration date.
- 7.3 The following is the report holder's contact information:

**CROSSFIELD PRODUCTS CORP. - MIRACOTE DIVISION**  
**3000 EAST HARCOURT STREET**  
**RANCHO DOMINGUEZ, CALIFORNIA 90221**  
**(310) 886-9100**  
[www.miracote.com](http://www.miracote.com)

**TABLE 1—MIRACOTE MIRAFLEX WATERPROOFINGSYSTEM APPLIED OVER PLYWOOD DECKS**

COMPONENT	SYSTEM A	SYSTEM B
Lath fastener	Staples	Staples
Expanded lath	1.8 lb/yd <sup>2</sup>	1.8 lb/yd <sup>2</sup>
Base coat	MiraPatch LM or MiraPatch RM 3	MiraPatch LM or MiraPatch RM 3
Waterproofing	Miraflex Membrane A	MiraFlex Liquid Membrane
Reinforcing fabric	Miracote Poly fabric	MiraFlex Seam Tape
Protection coat	Miracote MPC Protective Coating	Miracote MPC Protective Coating
Topcoat	Miracote MiraGard Color Bond (XL)	Miracote MiraGard Color Bond (XL)
Sealer	NA	Miracote Miragard HDWB

For **SI**: 1 lb/yd<sup>2</sup> = 0.537 kg/m<sup>2</sup>.

NA: Not applicable

RM: Repair Mortar

**TABLE 2—MIRACOTE MIRAFLEX WATERPROOFINGSYSTEM APPLIED OVER CONCRETE DECKS**

COMPONENT	SYSTEM D	SYSTEM E	SYSTEM F	SYSTEM G
Waterproofing	MiraFlex Membrane A	MiraFlex Membrane A	MiraFlex Membrane A	MiraFlex Membrane A
Protection coat	Miracote MPC Protective Coating	Miracote MPC Protective Coating	Miracote MPC Protective Coating	Mirastamp Coating
Topcoat	Miracote MiraGard Color Bond (XL)	Miracote MiraGuard Color Bond (XL)	NA	NA
Sealer	Miracote MiraGard HDWB	NA	Miracote MiraGard HDWB	Miracote MiraGard HDWB

NA: Not applicable.

**TABLE 3—MAXIMUM ULTIMATE DESIGN WIND SPEED FOR MIRACOTE MIRAFLEX WATERPROOFINGSYSTEMS  
[2012 IBC (miles per hour)]<sup>1,2,3,4</sup>**

Height, ft	Zone 1			Zone 2			Zone 3		
	Exp B	Exp C	Exp D	Exp B	Exp C	Exp D	Exp B	Exp C	Exp D
0-15	160	150	140	130	120	110	110	-	-
20	160	150	140	130	115	110	110	-	-
25	160	140	130	130	115	-	110	-	-
30	160	140	130	130	110	-	110	-	-
40	160	140	130	130	110	-	-	-	-
50	150	140	130	120	110	-	-	-	-
60	150	130	130	120	-	-	-	-	-

For **SI**: 1 ft = 304.8 mm 1 mph = 1.6 kph.

<sup>1</sup>The values are based on roofs with slopes not exceeding 7 degrees from horizontal, and the following conditions:

- G<sub>Cp</sub> = 2.8 for Zone 3
- G<sub>Cp</sub> = 1.8 for Zone 2
- G<sub>Cp</sub> = 1.0 for Zone 1
- G<sub>Cpi</sub> = +/-0.18

<sup>2</sup>Applicable for Risk Category II buildings, for a given location, the tabulated values must not exceed those shown in the 2012 IBC Figure 1609A.

<sup>3</sup>Zones 1, 2 and 3 are defined in IBC, IRC, and ASCE 7-10.

<sup>4</sup>For a given location, the tabulated values multiplied by a factor of  $\sqrt{0.6}$  must not exceed those shown in the 2012 IRC wind speed map.

**TABLE 4—MAXIMUM ALLOWABLE BASIC WIND SPEED FOR MIRACOTE MIRAFLEX WATERPROOFINGSYSTEMS  
[2009 and 2006 IBC, 3-sec gust (miles per hour)]<sup>1,2,3</sup>**

Height, ft	Zone 1			Zone 2			Zone 3		
	Exp B	Exp C	Exp D	Exp B	Exp C	Exp D	Exp B	Exp C	Exp D
0-15	130	120	110	105	95	85	85	-	-
20	130	120	110	105	90	85	85	-	-
25	130	110	100	105	90	-	85	-	-
30	130	110	100	105	85	-	85	-	-
40	130	110	100	100	85	-	-	-	-
50	120	110	100	95	85	-	-	-	-
60	120	100	100	95	-	-	-	-	-

For **SI**: 1 ft = 304.8 mm 1 mph = 1.6 kph.

<sup>1</sup>The values are based on roofs with slopes not exceeding 7 degrees from horizontal, and the following conditions:

- I = 1.0
- G<sub>Cp</sub> = 2.8 for Zone 3
- G<sub>Cp</sub> = 1.8 for Zone 2
- G<sub>Cp</sub> = 1.0 for Zone 1
- G<sub>Cpi</sub> = +/-0.18

<sup>2</sup>For a given location, the tabulated values must not exceed those shown in the 2009 and 2006 IBC/IRC wind speed maps.

<sup>3</sup>Zones 1, 2 and 3 are defined in IBC, IRC, and ASCE 7-05.

**DIVISION: 07 00 00—THERMAL AND MOISTURE PROTECTION**  
**Section: 07 18 13—Pedestrian Traffic Coatings**

**REPORT HOLDER:**

**CROSSFIELD PRODUCTS CORP. - MIRACOTE DIVISION**

**EVALUATION SUBJECT:**

**MIRACOTE MIRAFLEX WATERPROOFING DECKING SYSTEMS**

**1.0 REPORT PURPOSE AND SCOPE****Purpose:**

The purpose of this evaluation report supplement is to indicate that Miracote Miraflex Waterproofing Decking Systems, described in ICC-ES evaluation report ESR-1714, have also been evaluated for compliance with the codes noted below.

**Applicable code editions:**

- 2022 *California Building Code* (CBC)

For evaluation of applicable chapters adopted by the California Office of Statewide Health Planning and Development (OSHPD) AKA: California Department of Health Care Access and Information (HCAI) and the Division of State Architect (DSA), see Sections 2.1.1 and 2.1.2 below.

- 2022 *California Residential Code* (CRC)

**2.0 CONCLUSIONS****2.1 CBC:**

The Miracote Miraflex Waterproofing Decking Systems, described in Sections 2.0 through 7.0 of the evaluation report ESR-1714, comply with CBC Chapter 15, provided the design and installation are in accordance with the 2021 *International Building Code*® (IBC) provisions noted in the evaluation report and the additional requirements of CBC Chapters 15, 16 and 17, as applicable.

**2.1.1 OSHPD:**

The applicable OSHPD Sections and Chapters of the CBC are beyond the scope of this supplement.

**2.1.2 DSA:**

The applicable DSA Sections of the CBC are beyond the scope of this supplement.

**2.2 CRC:**

The Miracote Miraflex Waterproofing Decking Systems, described in Sections 2.0 through 7.0 of the evaluation report ESR-1714, comply with CRC Chapter 9, provided the design and installation are in accordance with the 2021 *International Residential Code*® (IRC) provisions noted in the evaluation report and additional requirements of CRC Chapter 9, as applicable.

This supplement expires concurrently with the evaluation report, ESR-1714, reissued May 2024 and revised January 2025.

**DIVISION: 07 00 00—THERMAL AND MOISTURE PROTECTION**  
**Section: 07 18 13—Pedestrian Traffic Coatings**

**REPORT HOLDER:**

**CROSSFIELD PRODUCTS CORP. - MIRACOTE DIVISION**

**EVALUATION SUBJECT:**

**MIRACOTE MIRAFLEX WATERPROOFING DECKING SYSTEMS**

**1.0 REPORT PURPOSE AND SCOPE****Purpose:**

The purpose of this evaluation report supplement is to indicate that the Miracote Miraflex Waterproofing Decking Systems, described in ICC-ES evaluation report ESR-1714, has also been evaluated for compliance with the codes noted below.

**Applicable code editions:**

- 2023 Florida Building Code—Building
- 2023 Florida Building Code—Residential

**2.0 CONCLUSIONS**

The Miracote Miraflex Waterproofing Decking Systems, described in Sections 2.0 through 7.0 of ICC-ES evaluation report ESR-1714, is a component of a Class A roof covering assembly, in compliance with the *Florida Building Code—Building* and the *Florida Building Code—Residential*. The design requirements must be determined in accordance with the *Florida Building Code—Building* and the *Florida Building Code—Residential*, as applicable. The installation requirements noted in ICC-ES evaluation report ESR-1714 for the 2021 *International Building Code*® meet the requirements of the *Florida Building Code—Building* and the *Florida Building Code—Residential*, as applicable.

Use of the Miracote Miraflex Waterproofing Decking Systems for compliance with the High-Velocity Hurricane Zone provisions of the *Florida Building Code—Building* or the *Florida Building Code—Residential* has not been evaluated, and is outside the scope of this supplemental report.

For products falling under Florida Rule 61G20-3, verification that the report holder's quality assurance program is audited by a quality assurance entity approved by the Florida Building Commission for the type of inspections being conducted is the responsibility of an approved validation entity (or the code official when the report holder does not possess an approval by the Commission).

This supplement expires concurrently with the evaluation report, ESR-1714, reissued May 2024 and revised January 2025.